

# Dedraflow® 2800

## Chemical Composition:

Component	Legislation
Hydrogenated Polyisobutene	CAS No. 68937-10-0
Dimethicone	CAS No. 9006-65-9 ; 9016-00-6 ; 63148-62-9 JSCI (104210)

**INCI Name:** Hydrogenated Polyisobutene (and) Dimethicone

## Technical Information:

<b>Appearance</b>	Colourless, clear liquid
<b>Odour</b>	Characteristic
<b>Flash Point</b>	84°C
<b>Viscosity (20°C) (Lamy Tve-05 – Spindle: MS-BV1000 – Speed: 200 rpm)</b>	2500 – 3500 mPa.s
<b>Density (20°C)</b>	0,9 – 1,0 g/cm <sup>3</sup>
<b>Refractive Index (20°C)</b>	1,397 – 1,405
<b>Shelf Life</b>	Minimum 3 years

**Description:** Dedraflow® products are Hydrogenated Polyisobutenes or mixtures of Hydrogenated Polyisobutenes and Silicone Oils. They vary from very volatile grades without residue to extremely viscous grades with substantial residue. Dedraflow® 2800 has high viscosity while still being pourable. It forms an occlusive film.  
Typical use level: 2-10%

Before using this material see the MSDS.  
This technical information is offered as a guide not a guarantee.

